

## Electrically conductive polyurethane hose, heavy

### Application

- flexible hose/ ducting for high throughput of abrasive powder, bulk material, granulate and for gases
- industrial vacuum cleaners, vacuum cleaners
- explosion hazard area
- Coal mine, mine, tunnelling: ventilation, methane extraction
- raw material conveying hose for powders, granulates, sand, quartz, gravel, shards and chips/ shavings

### Properties

- heavy duty
- increased pressure and vacuum resistance
- highly abrasion resistant

- very good low temperature flexibility
- good resistance to oil, gasoline and chemicals
- in accordance with ATEX 2014/34/EU (1999/92/EC) and German TRGS 727: pneumatic transport of flammable dusts and bulk materials (Zone 20, 21, 22 inside), aspiration of combustible dusts (Zone 22 inside),
- in accordance with ATEX 2014/34/EU (1999/92/EC) and German TRGS 727: for conveying for flammable liquids (inside zone 0, 1, 2), for conveying for non-flammable liquids, for use in zone 1 and 2 (gases), for use in zone 0 (gases)
- according to DIN 26057 Type 3
- conforms to RoHS guideline
- REACH according to --> Technology / Technical Information / REACH

### Temperature Range

- 40°C to 90°C

### Design

#### Design

- AIRDUC® profile hose
- spring steel wire firmly embedded in wall
- wall: electrically conductive premium ester-polyurethane (Pre-PUR®)
- wall thickness 1,4 - 1,5 mm approx.

#### Delivery variants

- further diameters and lengths available on request
- black (standard)
- customer-specific branding


I.D. (in / mm)	outer Ø (mm)	Pressure DIN 26057 (50% Elongation) (bar)	Vacuum DIN 26057 (axially fixed) (bar)	Bending Radius (mm)	Weight (kg/m)	Dimensions in Stock (m)	Order No.
1 / 25	32.00	2,930 (4,74)	0,950 (1,00)	20.00	0.28	10 15	355-0025-1003
- / 30	40.00	2,470 (3,99)	0,650 (1,00)	25.00	0.47	10 15	355-0030-1003
1,25 / 32	42.00	2,325 (3,75)	0,610 (1,00)	26.00	0.47	10 15	355-0032-1003
1,5 / 38	48.00	1,975 (3,19)	0,515 (1,00)	29.00	0.55	10 15	355-0038-1003
- / 40	50.00	1,880 (3,03)	0,490 (1,00)	30.00	0.57	10 15	355-0040-1003
2 / 50-51	60.00	1,515 (2,45)	0,390 (1,00)	35.00	0.71	10 15 20	355-0050-1003
- / 55	65.00	1,385 (2,23)	0,355 (1,00)	38.00	0.77	10 15	355-0055-1003
2,36 / 60	70.00	1,270 (2,05)	0,325 (1,00)	40.00	0.83	10 15 20	355-0060-1003
2,5 / 63-65	75.00	1,175 (1,90)	0,300 (1,00)	43.00	0.89	10 15	355-0065-1003
- / 70	81.00	1,515 (2,45)	0,250 (1,00)	62.00	1.01	10 15	355-0070-1003
3 / 75-76	86.00	1,420 (2,29)	0,235 (1,00)	66.00	1.07	10 15	355-0075-1003
- / 80	91.00	1,335 (2,15)	0,220 (1,00)	69.00	1.14	10 15	355-0080-1003
3,5 / 89-90	101.00	1,190 (1,92)	0,195 (1,00)	76.00	1.27	10 15	355-0090-1003
4 / 100	111.00	1,075 (1,73)	0,175 (0,94)	83.00	1.41	10 15	355-0100-1003
- / 110	121.00	0,980 (1,58)	0,160 (0,77)	90.00	1.54	10 15	355-0110-1003
4,5 / 114-115	126.00	0,935 (1,51)	0,155 (0,70)	94.00	1.61	10 15	355-0115-1003
5 / 125-127	136.00	0,865 (1,39)	0,140 (0,59)	101.00	1.74	10 15	355-0125-1003
6 / 150-152	161.00	0,720 (1,16)	0,130 (0,55)	118.00	2.29	10 15	355-0150-1003

Overpressure and underpressure are recommended threshold operating values, products can be subjected to higher loads upon request. The bending radius is measured through the inside of the hose arch. The right to make technical modifications is reserved. All values determined at 20°C and are approx. data. Additional information at [www.norres.com/en/technology/](http://www.norres.com/en/technology/)


I.D. (in / mm)	outer Ø (mm)	Pressure DIN 26057 (50% Elongation) (bar)	Vacuum DIN 26057 (axially fixed) (bar)	Bending Radius (mm)	Weight (kg/m)	Dimensions in Stock (m)	Order No.
8 / 200	212.00	0,505 (0,81)	0,085 (0,38)	155.00	2.85	10	355-0200-1003
- / 300	313.00	0,340 (0,54)	0,075 (0,27)	226.00	4.32	10	355-0300-1003
- / 315	328.00	0,320 (0,52)	0,070 (0,25)	237.00	4.64	10	355-0315-1003

Overpressure and underpressure are recommended threshold operating values, products can be subjected to higher loads upon request. The bending radius is measured through the inside of the hose arch. The right to make technical modifications is reserved. All values determined at 20 °C and are approx. data. Additional information at [www.norres.com/en/technology/](http://www.norres.com/en/technology/)

## Accessories



CONNECT 228



CONNECT 244



CONNECT 245



CLAMP 213



CLAMP 212 EC



CONNECT 246 AS



CLAMP 216



CONNECT 223



CONNECT 240 EC



CONNECT MOULD ASSEMBLY 233



CONNECT SAFETY CLAMP ASSEMBLY 231



CONNECT 240 + 241 AS



CONNECT 242



CLAMP 212



CONNECT PRESS ASSEMBLY 232



CONNECT 243



CLAMP 217



CONNECT THREAD FITTING 234



CONNECT 270-271

Overpressure and underpressure are recommended threshold operating values, products can be subjected to higher loads upon request. The bending radius is measured through the inside of the hose arch. The right to make technical modifications is reserved. All values determined at 20 °C and are approx. data. Additional information at [www.norres.com/en/technology/](http://www.norres.com/en/technology/)